

ART. 126/30/AU

CAFIPOR20/10

COMPOSITION	Polyurethane foam self-extinguishing								
CELL TEXTURE	opened								
COLOUR	black								
TECHNICAL SPECIFICATIONS	MEASURE UNIT	TEST METHOD	POROSITY						
DENSITY	kg/mc	//	10	20	30	45	60	75	90
COMPRESSIVE STRENGTH -40%	kPA	ISO 3386	32-36	32-36	32-36	32-36	32-36	32-36	32-36
MAXIMUM ELONGATION	%	ISO 1798	2,5-4,5	2,5-4,5	2,5-4,5	2,5-4,5	2,5-4,5	2,5-4,5	2,5-4,5
TENSILE STRENGTH	kPA	ISO 1798	>150	>200	>250	>250	>250	>250	>250
CELL PORES	PPI	SS/T.013.3	>60	>100	>130	>150	>150	>150	>150
TEMPERATURE RESISTANCE	- 40 / + 100 °C		7-15	15-25	25-35	35-50	50-65	65-80	85-95
SELF EXTINGUISHING NORM REF.	FMV SS 302								